

KANSAI POLYESTER PUTTY BPO 2 Kg SET

Code: 223-117

AUTO REFINISH

PUTTY 2K

DESCRIPTION

It is a two component (2K) Polyester Putty with BPO as a curing system hardener.

USE

It is suitable for the surface of various metal ground materials including galvanized sheet. It is especially suitable for quick repair and repair of automobile.

CHARACTERISTICS

1. Short drying time
2. Quick to polish
3. Easy application
4. Good adhesion
5. Best adhesion on zinc plate

COLOR AND GLOSS LEVEL APPEARANCE

Yellowish white, uniform and dense without coarse material

BASIC DATA

Data for mix product	
Number of components	Two
Application Method	Scraping
Specific Gravity	1.07 g/ml (depend on colors)
Film Appearance	Uniform color, smooth & no crack
Density	1.6 - 1.8 gr/cm ³
Scraping time	No more than 6 minutes, until it can not be scraped
Sanding time	< 30 minutes
Sanding property	It is easy to grind with p80 sandpaper
Base / Hardener	100 / 1 - 2.5
Pot Life	4 - 6 minutes (30°C)
Storage	Store in cool, dry conditions in the original containers.
Packaging	Base : 2 Kg Hardener : 50 gram

SURFACE PREPARATION

All surface to be coated should be completely clean, dry and free from contamination.

APPLICATION

Equipment Use	Volume of thinner	Recommended thinner	Application method
Squeegee or putty knife	Without thinner	-	Apply a thin initial coat to fill minor holes and scratch marks. Extra thin layers can be applied with an interval of 4 to 6 minutes

Drying time			
Substrate temperature	Set to touch	Semi dry	Hard dry
30°C	5 minutes	15 minutes	30 minutes

SAFETY PRECAUTIONS

For paint and recommended thinners see safety sheet and relevant material safety data sheets. This is a solvent borne paint and care should be taken to avoid inhalation of spray mist or vapor as well as contact between the wet paint and exposed skin or eyes

- Flammable liquid and vapor, concentrating of its vapor may cause explosion
- Harmful if swallowed. May causes eyes, skin and respiratory tract irritation.
- May cause long term adverse effect in the aquatic environment

DISCLAIMER

Spreading rate, drying time, and other numerical parameters are based on controlled environment test and evaluation. It may vary on actual usage due to differences on surface type and porosity, surrounding humidity and temperature, painters' skill and equipment, and other external factors. User should always consult with Kansai Paint for specific guidelines on particulars paint jobs for the best result. All information can be adjusted accordingly without further notice.