

KANSAI SUPERSEAL PU

CODE : 391-001/002

PROTECTIVE COATING

POLYURETHANE WATERPROOFING

DESCRIPTION

Two component high solid elastic weathering aliphatic polyaspartic coatings (Hybrid Polyurea)

USE

Waterproofing for interior-exterior concrete and metal substrate, crack bridging coating

COLOR AND GLOSS LEVEL APPEARANCE

- Grey
- Gloss Level : Gloss

BASIC DATA

Data for mix product	
Application Method	Airless spray, Air spray, Brush or Roller
Specific Gravity	1.58 g/ml (mixtures)
Volume Solids	95% (mixtures)
VOC	79 g/Liter (Method 24 analysis)
Flash point	Base : 28°C Hardener : 284°C
Mixing Ratio	Base : Hardener = 100 : 40 by weight
Recommended DFT	1000 micron/ coat (by Trowell)
Theoretical coverage	1 m ² /Kg at DFT 1000 micron 1.5 m ² /Liter at DFT 100 micron *Practical coverage vary depending on loss factor
Pot Life	At temperature 10°C 20°C 30°C 1 hours 40 min 30 min *Use all mixed paint within pot life
Working Time	15 minutes at 30°C
Elongation	180% at 1 mm thickness
Packaging	5 Kg (4.03 Liter) Base in 5 Liter container 1 Kg (0.95 Liter) Hardener in 1 Liter container

SURFACE PREPARATION SUMMARY TABLE

Substrate	Surface Preparation	
	Minimum	Recommended
Carbon Steel	St 3 (ISO 8501-1)	Sa 2 ½ (ISO 8501-1)
Concrete	Clean, dry and undamaged concrete. New concrete shall be cure at least 28 days	Clean, dry and undamaged concrete. New concrete shall be cure at least 28 days
Coated Surfaces	Clean, dry and undamaged compatible coating	Clean, dry and undamaged compatible coating

APPLICATION

Ambient temperature shall be above 5°C and relative humidity shall be below 85%. Surface temperature shall be minimum of 3°C above dew point. Adequate ventilation shall be provided in confined spaces to ensure proper drying.

Mixing	This material is a two component coating. Always mix a complete set unit in the proportion supplied. After mix, use all mixed paint within pot life specified 1). Stir Base (Part A) with power agitator 2). Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator	
Airless Spray	Recommended	Nozzle Tip : 0.33 – 0.48 mm Nozzle Pressure : Not less than 10MPa
Air Spray (Conventional)	Recommended	Nozzle Size : 1.5 – 2 mm Nozzle Pressure : 0.3 – 0.4 MPa
Brush	Recommended	Typically 20 – 30 μ can be achieved
Roller	Recommended	Typically 20 – 30 μ can be achieved
Trowell	Recommended	Typically 1000μ can be achieved
Thinner	No Thinning	No Thinning

Over coating interval for DFT 1000 micron				
Over-coating with	Interval	10°C	20°C	30°C
Polyurethan coating	Minimum	72 hours	48 hours	24 hours
	Maximum	1 month	1 month	1 month

Curing time DFT to 1000 micron			
Substrate temperature	Dry to touch	Dry to handle	Full cure
10°C	12 hours	48 hours	7 days
20°C	8 hours	24 hours	7 days
30°C	6 hours	16 hours	7 days

SAFETY PRECAUTIONS

For paint and recommended thinners, see safety sheet and relevant material safety data sheet. This is a solvent borne paint and care should be taken to avoid inhalation of spray mist of vapor as well as contact between the wet paint and exposed skin or eyes.

- Avoid at all times inhalation or aerosol spray-mist
- Harmful by inhalation and in contact with skin
- Highly flammable liquid and vapor
- Harmful to aquatic organism, may cause long-term adverse effects in the aquatic environment

STORAGE

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed. Store conditions shall be in accordance with national regulations.

DISCLAIMER

The information given on this sheet is the best of our knowledge and accuracy at the time of issuing. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development.