

RABAMARINE PAINT

CODE : 413-XXX

PROTECTIVE COATING

CHLORINATED RUBBER

DESCRIPTION

A Chlorinated rubber weathering resistance enamel paint

USE

Topcoat for super structure exterior deck fittings, light metal

COLOR AND GLOSS LEVEL APPEARANCE

- White, and custom color (by request)
- Gloss Level : Sheen, Matt (by request)

BASIC DATA

Data for mix product	
Application Method	Airless spray, Air spray, Brush or Roller
Specific Gravity	1.28 g/ml (White color)
Volume Solids	56.00%
VOC	563 g/Liter (Method 24 analysis)
Flash point	42°C
Recommended DFT	35 micron/ coat
Theoretical Coverage	12 m ² /Liter at DFT 35 micron 9.37 m ² /Kg at DFT 35 micron *Practical coverage vary depending on loss factor
Packaging	5 Liter (6.4 Kg) in 5 Liter container 20 Liter (25.6 Kg) in Pail can

SURFACE PREPARATION SUMMARY TABLE

Substrate	Surface Preparation	
	Minimum	Recommended
Coated Surfaces	Clean, dry and undamaged compatible coating. Soft sanding if necessary	Clean, dry and undamaged compatible coating. Soft sanding if necessary

APPLICATION

Ambient temperature shall be above 5°C and relative humidity shall be below 85%. Surface temperature shall be minimum of 3°C above dew point.

Adequate ventilation shall be provided in confined spaces to ensure proper drying

Mixing	This material is a one component coating. Stir paint in container with power agitator well before using	
Airless Spray	Recommended	Nozzle Tip : 0.33 – 0.53 mm Nozzle Pressure : Not less than 10MPa
Air Spray (Conventional)	Recommended	Nozzle Orifice : 1.5 – 2 mm Nozzle Pressure : 0.3 – 0.4 MPa
Brush	Recommended	Typically 20 – 30μ can be achieved
Roller	Recommended	Typically 20 – 30μ can be achieved
Thinner	Rabamarine Thinner	Max 10% depend on application method

Over coating interval for DFT 35 micron				
Over-coating with	Interval	10°C	20°C	30°C
Chlorinated rubber	Minimum	16 hours	12 hours	8 hours
	Maximum	1 month	1 month	1 month

Curing time DFT to 35 micron			
Substrate temperature	Dry to touch	Dry to handle	Full cure
10°C	12 hours	48 hours	7 days
20°C	10 hours	24 hours	7 days
30°C	6 hours	16 hours	7 days

SAFETY PRECAUTIONS

For paint and recommended thinners, see safety sheet and relevant material safety data sheet

This is a solvent borne paint and care should be taken to avoid inhalation of spray mist of vapor as well as contact between the wet paint and exposed skin or eyes

- Avoid at all times inhalation or aerosol spray-mist
- Harmful by inhalation and in contact with skin
- Highly flammable liquid and vapor
- Harmful to aquatic organism, may cause long-term adverse effects in the aquatic environment

STORAGE

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed. Store conditions shall be in accordance with national regulations

DISCLAIMER

The information given on this sheet is the best of our knowledge and accuracy at the time of issuing. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development.