

UNISTAIN SERIES

Code: 288-XXX

WOOD FINISH

STAIN

DESCRIPTION

An universal solvent based dyestuff colorant

USE

As colorant for wooden and rattan substrate

PRODUCT FEATURES

1. Easy to apply
2. Good transparency
3. Good tinting strength
4. Can be mix with general solvent-based paint

APPEARANCE

Transparent color

BASIC DATA

	Specification
Solid Content	2 - 5 %
Supply Viscosity (25°C)	-
Specific Gravity	0.85 - 0.92
Packaging	20 Liter

APPLICATION

Recommended MC Wood	8 - 12 %
Recommended Room Humidity	60 - 70 %
Recommended Room Temperature	26 - 30°C
Application Method	Air spray, Wiping
Thinner	General lacquer thinner
Mixing Ratio (by volume) - Base / Thinner	100 / 100-200 depend on color density
Spray Viscosity	-
Recommended DFT	-
Drying Time (30°C)	1 hours
Blocking resistance	-
Packing Time	-
Coverage by spray	-

PRODUCT SERIES

Product Code & Name	
288-703 Unistain Walnut	288-716 Unistain Tosca
288-709 Unistain Red	288-719 Unistain Kazama Brown
288-710 Unistain Orange	288-823 Unistain SHP Brown
288-711 Unistain Black	288-826 Unistain Salak Brown
288-712 Unistain Yellow	288-850 Unistain Bright Honey
288-713 Unistain Pecan	288-887 Unistain Crafter Mahogani
288-714 Unistain Light Honey	288-XXX Unistain Custom Color
288-715 Unistain Grasshoper	

SAFETY PRECAUTIONS

- For paint and recommended thinners see safety sheet and relevant material safety data sheets. This is a solvent borne paint and care should be taken to avoid inhalation of spray mist or vapor as well as contact between the wet paint and exposed skin or eyes
- Avoid at all times inhalation or aerosol spray-mist
 - Harmful by inhalation and in contact with skin, highly flammable liquid and vapor, may cause cancer and genetic defects
 - Harmful to aquatic organisms, may cause long-term adverse effects in the aquatic environment

DISCLAIMER

The information and numerical parameters are based on controlled environment test and evaluation, it may vary on actual usage due to differences on surface type and porosity, surrounding humidity and temperature, painter skill and equipment, and other external factors. User should always consult with Kansai Paint for specific guidelines on particular paint jobs for the best result. All information can be adjusted accordingly without further notice.