

# VINY PLAMUR

Code: 247-014

DECORATIVE

WATER BASED PRIMER

## DESCRIPTION

A general-purpose putty based on a special synthetic emulsion resin and extenders, formulated for leveling both interior and exterior surfaces.

## USE

For filling and leveling minor imperfections on a wide range of interior and exterior surfaces, including concrete, brick, asbestos, hardboard, and plywood, to create a smooth surface.

## FEATURES AND BENEFITS

1. Level uneven surface
2. Easy to sand
3. Great bond to wall surface
4. Easy to apply
5. Quick dry

## COLOR AND GLOSS LEVEL APPEARANCE

- White
- Gloss level: Matt

## BASIC DATA

Data for mix product	
Number of components	One
Application Method	Spatula
Specific Gravity (ASTM D1475)	1.66 g/ml
Volume Solids (ISO 3233)	47%
Flash Point (ASTM D3278)	-
VOC (ISO 11890-2)	<5 g/Liter
Mixing Ratio	-
Thinner	Clean water
Thinning ratio	-
Recommended DFT	-
Theoretical coverage	8 - 10 m <sup>2</sup> /Liter at DFT 15 - 20 micron
Overcoating Interval	-
Packaging	At temperature 30°C Minimum : 6 hours Maximum : 2 days
Packaging	5 Kg in plastic container & 25 Kg in pailcan

## SURFACE PREPARATION

- All surface to be coated should be completely clean, dry and free from contamination
- Remove salt and other water-soluble contaminants by fresh water
- Remove oil and grease with suitable detergents or solvent

## APPLICATION

Equipment Use	Volume of thinner	Recommended thinner	Nozzle orifice	Nozzle pressure
Air spray	-	-	-	-
Airless spray	-	-	-	-
Roller	-	-	-	-
Spatula	-	-	-	-

Painting Process	Interval	Recommended Topcoat	
		New Wall	Re-Painting
Primer	-	KANSAI PROPERTY KANSAI ANTI-MOSQUITO KANSAI TROPIC KANSAI OK-100	
Coat 1	-		
Coat 2	-		

Curing time DFT to 25 - 30 micron			
Substrate temperature	Dry to touch	Dry to handle	Full cure
5°C (41°F)	-	-	-
20°C (50°F)	-	-	-
30°C (68°F)	1 hours	6 hours	3 days

## SAFETY PRECAUTIONS

For paint and recommended thinner see safety sheet and relevant material safety data sheets. This is a solvent borne paint and care should be taken to avoid inhalation of spray mist or vapour as well as contact between the wet paint and exposed skin or eyes.

- Avoid at all time inhalation or aerosol spraymist

## DISCLAIMER

Spreading rate, drying time, and other numerical parameters are based on controlled environment test and evaluation. It may vary on actual usage due to differences on surface type and porosity, surrounding humidity and temperature, painters' skill and equipment, and other external factors. User should always consult with Kansai Paint for specific guidelines on particulars paint jobs for the best result. All information can be adjusted accordingly without further notice.